

# DATA SHEET

## MZ97B

Wide temperature and low loss material,

recommended to use at frequencies of 100KHz~300KHz.

2023/03/27



高科磁技股份有限公司  
中鋼集團

## Materials specification

MZ97B

## MZ97B SPECIFICATIONS

	CONDITIONS	VALUE	UNIT
$\mu_i$	25°C; $\leq 10$ kHz; 0.25mT	$3500 \pm 20\%$	
$\mu_a$	25°C; $\leq 25$ kHz; 200mT	5200	
Bs	25°C; 10 kHz; 1200A/m 100°C; 10 kHz; 1200A/m	530 420	mT
Br	25°C; 10 kHz; 1200A/m 100°C; 10 kHz; 1200A/m	80 70	mT
Hc	25°C; 10 kHz; 1200A/m 100°C; 10 kHz; 1200A/m	10 9	A/m
Pv	25°C; 100kHz; 200mT 60°C; 100kHz; 200mT 120°C; 100kHz; 200mT 140°C; 100kHz; 200mT	265 250 315 370	kW/m <sup>3</sup>
$\rho$	DC; 25°C	5	$\Omega \cdot m$
Tc		$\geq 215$	°C
Density		4850	kg/m <sup>3</sup>




Fig.1 Complex permeability as a function of frequency.




Fig.2 Amplitude permeability as function of peak flux density.




Fig.3 Initial permeability as a function of temperature.

## Materials specification

MZ97B




Fig.4 Specific power loss as a function of peak flux density with frequency as a parameter.




Fig.5 Specific power loss for several frequency/flux density combinations as a function of temperature.




Fig.6 Typical B-H loops of 25°C & 100°C




Fig.7 Bs VS Temperature