

DATA SHEET

NZ200

Materials specification

2024/09/01



高科磁技股份有限公司
中鋼集團

NZ200 SPECIFICATIONS

Initial permeability	μ_i	-	f=10kHz	0.25mT	25°C	2000±25%
Remanent flux density	Br	mT		4000A/m	25°C	50
Coercive Force	Hc	A/m				20
Saturation magnetic flux density	Bs	mT				320
Temperature factor of initial permeability		$\times 10^{-6}/^{\circ}\text{C}$	f=10kHz	0.25mT	25 to 60°C	2 to 7
Relative loss factor	$\tan\delta/\mu_i$	$\times 10^{-6}$	f=10kHz	0.25mT	25°C	<15
			f=500kHz			<50
Curie temperature	Tc	°C	f=10kHz	0.25mT		>120
Resistivity	ρ	Ωm			25°C	>10 ⁵
Density	kg/m ³					>5.1×10 ³

